

Comp Coat 80

1. PRODUCT DESCRIPTION

Ceratech's Comp Coat 80 is an emulsion of high grade acrylic resins in water. It dries by evaporation to yield a tough, velvety, non-yellowing, water repellent surface with exceptional mildew resistance and ultra-violet light stability.

Unlike other coatings, Ceratech Comp Coat 80 has unique binders that bite into the composition shingle, and at the same time rejuvenates and lubricates to keep composition shingles soft, pliable and intact. Comp Coat 80 will not dry out or cause the roof to cure up and delaminate. Ceratech Comp Coat 80 provides long durability, mildew resistance and protection for many years.

It is applied to yield a tough, watertight, roof membrane. Ceratech Comp Coat 80 will take all universal tints. Ask your local distributor for more information.

2. OUTSTANDING FEATURES

Non-toxic	UV Resistant
Water Borne	Abrasion Resistant
Energy Savings	Flexible
Launderable	Ten (10) year Warranty
Non-yellowing	Labor, Time, & Cost Saving
Mildew Resistant	Clean up with soap & water

3. APPLICATION

Surfaces should be clean, dry and sound. Existing surface dirt, oil, tar, grease and film should be removed from surface by approved methods prior to application. See Application Specifications in the distributor manual for your particular application.

Ceratech Elastomeric Comp Coat 80 can be applied by brush, roller or airless spray equipment. It should be applied evenly without buildup. Comp Coat 80 is used as a primer coat and should be top coated with Pond Coat 30.

4. CAUTIONS AND WARNINGS

Do not take internally. Avoid contact with eyes. If solution does come in contact with eyes, flush immediately with water and contact physician for medical attention. Avoid prolonged contact with skin or breathing of spray mist. **KEEP OUT OF THE REACH OF CHILDREN. KEEP FROM FREEZING.**

5. TYPICAL PERFORMANCE PROPERTIES

Weatherability

No blistering, cracking or delaminating/2000 hours accelerated weathering. ASTM E-42 or (G-26)

Fire Resistance

Flame spread	5	ASTM E-84-81A
Fuel Contribution	0	
Smoke Density	0	

Fungal Resistance

No fungal growth on sample	Tropical chamber
	ASTM D-3273-73T

Water Vapor Transmission

(Grains/Hr./Ft.)	Perms	
.6	.7	ASTM E96

COVERAGE CHART

Surface	Approx. Cov. (Sq.Ft.Per Gal)
---------	---------------------------------

Comp Roofing	80-100
Roll Roofing & Mineral Cap	80-100

Coverages are based on 1 gallon units and single coat applications. Coverages are approximate for normal substrates. Under irregular conditions more product is required.