

Rust Converter Metal Coat 901H

1. PRODUCT DESCRIPTION

Ceratech's Rust Converter Metal Coat 901H is an emulsion of high grade acrylic resins in water. It dries by evaporation to yield a tough, velvety, non-yellowing, water repellent surface with exceptional abrasion resistance and ultra-violet light stability. Ceratech Rust Converter Metal Coat 901H when applied directly to rust, will immediately convert iron oxide to iron sulfate upon contact, preventing further rusting problems. It is applied to yield a tough, watertight, roof membrane.

Ceratech's Rust Converter Metal Coat 901H will take all universal tints. Ask your local distributor for more information.

2. OUTSTANDING FEATURES

Non-toxic	Converts Rust
Water Borne	Abrasion Resistant
Mildew Resistant	Labor, Time, & Cost Saving
Launderable	Clean up with soap & water
Elasomeric	Ten (10) year Warranty

3. APPLICATION

Surfaces should be clean, dry and sound. Existing surface dirt, oil, tar, grease and film should be removed from surface by approved methods prior to application of Ceratech's Rust Converter Metal Coat 901H

Ceratech's Rust Converter Metal Coat 901H can be applied by brush, roller or airless spray equipment. It should be applied evenly without buildup. Multiple coats are recommended. See Application Specifications in the distributor manual for your particular application.

4. CAUTIONS AND WARNINGS

Do not take internally. Avoid contact with eyes. If solution does come in contact with eyes, flush immediately with water and contact physician for medical attention. Avoid prolonged contact with skin or breathing of spray mist. **KEEP OUT OF THE REACH OF CHILDREN. KEEP FROM FREEZING.**

5. TYPICAL PERFORMANCE PROPERTIES

Elongation	
236% at 77°F	ASTM D-412
211% at 32°F	

Tensile Strength	
406 P.S.I. at 77°F	ASTM D-412
339 P.S.I. at 32°F	

Abrasion Resistance	
No Wear after 450 liters ASTM D-968 of falling sand	

Visual Color	
9	ASTM D1729

Chalking	
10	ASTM D4214

Checking	
10	ASTM D660

Cracking	
10	ASTM D661

Blistering	
8	ASTM D714

Flaking	
10	ASTM D772

Accelerated Weathering	
2000 HRS. Pass	ASTM D4587

COVERAGE CHART

Surface	Approx. Cov. (Sq.Ft.Per Gal)
---------	---------------------------------

Metal	75-125
-------	--------

Coverages are based on 1 gallon units and single coat applications. Coverages are approximate for normal substrates. Under irregular conditions more product is required.